

Park Advanced Circuitry Materials

Nelco® N9000-13 RF

PTFE Performance Blended Laminate



The Nelco® N9000-13 RF is a next generation PTFE Performance Blended product which combines the RF electrical properties of PTFE with the competitive performance features of Nelco's proprietary N4000-13 epoxy.

Key Features

Blended material offers the mechanical performance of a thermoset epoxy with the electrical performance of PTFE

- Lead-free assembly compatibility.
- Excellent for cost-sensitive applications such as LNB's, In-building antennas and automotive telematics.
- Does not use expensive and abrasive ceramic fillers
- Provides a UL 94V-0 flammability rating.

CAF* Resistant

- Providing long term reliability in end products.

Standard constructions for a wide range of applications

Dielectric Constant**	Dissipation Factor**	Laminate Core Thickness
3.00	0.0040	0.020", 0.030", 0.060
3.20	0.0045	0.020", 0.030", 0.060
3.38	0.0046	0.020", 0.030", 0.060
3.50	0.0055	0.020", 0.030", 0.060

Optimized N9000 PTFE processing

- Conventional PTFE processing
- Most epoxy prepregs will adhere for hybrid multilayer applications

Global Availability

- Vacuum laminated
- Available worldwide
- Meets UL 94V-0 specifications
- All materials are RoHS compliant

Applications

- Antennas
- Automotive
- LNBs
- Hybrid RF Multilayers
- Avionics
- Military
- Commercial RF Applications
- Lead-Free Assembly Substrates

Global Availability

Nelco Products, Inc. (California) - Americas
+1.714.879.4293

Neltec, Inc. (Arizona) - Americas
+1.480.967.5600

Nelco Products Pte. Ltd. - Asia Pacific
+65.6861.7117

Neltec, S.A. - Europe
+33.562.98.52.90

www.parkelectro.com

info@parkelectro.com

Park's UL file number: E36295

**All Dk and loss testing performed according to IPC TM 650 testing methods at 10 GHz.

МЕХНОЛОГИЯ

Nelco® N9000-13 RF

PTFE Performance Blended Laminate

Property / Condition	Value (U.S. Units)		Value (Metric Units)		Test Method
Mechanical Properties					
Peel Strength - 1 oz. (35 micron) Cu					
After Solder Float	9.12	lb / inch	1.60	N / mm	IPC-TM-650.2.4.8
At Elevated Temperature	8.54	lb / inch	1.50	N / mm	IPC-TM-650.2.4.8.2a
After Exposure to Process Solutions	N/A	lb / inch	N/A	N / mm	IPC-TM-650.2.4.8
X / Y CTE [-40°C to +125°C]			13 - 20	ppm / °C	IPC-TM-650.2.4.41
Z Axis Expansion [-40°C to +125°C]			67	ppm / °C	Internal Method
Electrical Properties					
Dielectric Constant @ 10 GHz (Stripline)					IPC-TM-650.2.5.5.5
N9300-13 RF	3.00		3.00		
N9320-13 RF	3.20		3.20		
N9338-13 RF	3.38		3.38		
N9350-13 RF	3.48		3.48		
Dissipation Factor @ 10 GHz (Stripline)					IPC-TM-650.2.5.5
N9300-13 RF	0.0040		0.0040		
N9320-13 RF	0.0045		0.0045		
N9338-13 RF	0.0046		0.0046		
N9350-13 RF	0.0055		0.0055		
Volume Resistivity					
C - 96 / 35 / 90			10 ⁸	Mμ - cm	IPC-TM-650.2.5.17.1
E - 24 / 125			10 ⁹	Mμ - cm	IPC-TM-650.2.5.17.1
Surface Resistivity					
C - 96 / 35 / 90	10 ⁶	Mμ	10 ⁶	Mμ	IPC-TM-650.2.5.17.1
E - 24 / 125	10 ⁷	Mμ	10 ⁷	Mμ	IPC-TM-650.2.5.17.1
Electric Strength	1300	V / mil	4.8x10 ⁴	V / mm	IPC-TM-650.2.5.6.2
Dielectric Breakdown	>50	kV	>50	kV	IPC-TM-650.2.5.6
Arc Resistance	77	seconds	77	seconds	IPC-TM-650.2.5.1
Thermal Properties					
Glass Transition Temperature (T _g)					
DSC (°C)	428	°F	220	°C	IPC-TM-650.2.4.25c
TMA (°C)	410	°F	210	°C	IPC-TM-650.2.4.24c
DMA (°C)	473	°F	245	°C	IPC-TM-650.2.4.24.3
Degradation Temp (TGA) (5% wt. loss)	662	°F	350	°C	IPC-TM-650.2.4.24.6
Pressure Cooker - 60 min then solder dip					IPC-TM-650.2.6.16
@288°C until failure (max 10 min.)	600+	seconds	600+	seconds	(modified)
T ₂₆₀	30+	minutes	30+	minutes	IPC-TM-650.2.4.24.1
T ₃₀₀	8.7	minutes	8.7	minutes	IPC-TM-650.2.4.24.1
Chemical / Physical Properties					
Moisture Absorption	0.07	wt. %	0.07	wt. %	IPC-TM-650.2.6.2.1

Park Electrochemical Corp. is a global advanced materials company which develops and manufactures high-technology digital and RF/microwave printed circuit materials and advanced composite materials, parts and assemblies. The company operates under the Nelco®, Nelcote® and Nova™ names.

All test data provided are typical values and not intended to be specification values. For review of critical specification tolerances, please contact a Nelco representative directly. Nelco reserves the right to change these typical values as a natural process of refining our testing equipment and techniques.

Aeroglide™, CoreFix®, Essycure™, EF®, EP™, LD®, Mercurywave™, Nelco®, Nelcote®, Nova™, PeelCote™, RTFoil® and SI® are trademarks of Park Electrochemical Corp.

*CAF resistance has been established to greater than 500 hours using a specific OEM coupon design and test procedure. For details on this or other CAF tests, please visit www.parkelectro.com.

Nelco reserves the right to make changes without further notice to any products herein to improve reliability, function or design. Nelco does not assume any liability arising out of the application or use of any product described herein, neither does it convey any license under its patent rights nor the rights of others. This disclaimer of warranty is in lieu of all warranties whether expressed, implied or statutory, including implied warranties of merchantability or fitness for a particular purpose.



PARK
ELECTROCHEMICAL
CORP.